

Technical Information

CL7450

Property	Unit	Standard	Data
Material-Composition	%		ca.50 Polyamide/ ca.50 Polyurethane
Width	cm		≥120
Weight ¹	g/m ²		165±20
Thickness ²	mm		0.35±0.05
Breaking strength			
Lengthwise	kg/2.5 cm	JIS L1096	≥ 5
Crosswise	kg/2.5 cm	JIS L1096	≥ 4
Tear strength			
Lengthwise	kg	JIS L1096 A-1	≥ 1
Crosswise	kg	JIS L1096 A-1	≥ 1

Note: Above values are mean values

JIS = Japanese Industrial Standard

1) inhouse test

2) inhouse test with HOREX gauge

(These values cannot be guaranteed and may be changed depending on market and production requirements)

Status: July 2017