

## **Technical Information**

### **KX 8060**

<b>Property</b>	<b>Unit</b>	<b>Standard</b>	<b>Data</b>
Material-Composition	%		ca.60 Polyamide/ ca.40 Polyurethane
Width	cm		≥140
Weight <sup>1</sup>	g/m <sup>2</sup>		220±30
Thickness <sup>2</sup>	mm		0.65±0.10
Breaking strength			
Lengthwise	kg/2.5 cm	JIS L1096	≥ 10
Crosswise	kg/2.5 cm	JIS L1096	≥ 8
Tear strength			
Lengthwise	kg	JIS L1096 A-1	≥ 2.0
Crosswise	kg	JIS L1096 A-1	≥ 1.5
Pilling (Martindale)		ISO 12945-2	≥ 4
Colour fastness to light		ISO 105-B02	4

Note: Above values are mean values

JIS = Japanese Industrial Standard

1) inhouse test

2) inhouse test with HOREX gauge

(These are average physical property data for your reference only.

Each colour should be tested according to the customer's specifications.)

Status : November 2018