

Technical Information

KX/KS/KC7400

Property/	Unit/	Standard	Data
Material-Composition	%		ca.60 Polyamide/ ca.40 Polyurethane
Width	cm		≥ 130
Weight ¹	g/m ²		137±15
Thickness ²	mm		0.40±0.05
Breaking strength			
Lengthwise	kg/2.5 cm	JIS L1096	≥ 5
Crosswise	kg/2.5 cm	JIS L1096	≥ 4
Tear strength			
Lengthwise	kg	JIS L1096 A-1	≥ 0.8
Crosswise	kg	JIS L1096 A-1	≥ 0.7

Note: Above values are mean values

JIS = Japanese Industrial Standard

1) inhouse test

2) inhouse test with HOREX gauge

(These values cannot be guaranteed and may be changed depending on market and production requirements)

Status : January 2018