

## Technical Information

### KX / KS / KC 7500

Property/	Unit/	Standard	Data
Material-Composition	%		ca.60 Polyamide/ ca.40 Polyurethane
Width	cm		≥130
Weight <sup>1</sup>	g/m <sup>2</sup>		190±30
Thickness <sup>2</sup>	mm		0.55±0.10
Breaking strength			
Lengthwise	kg/2.5 cm	JIS L1096	≥ 9
Crosswise	kg/2.5 cm	JIS L1096	≥ 7
Tear strength			
Lengthwise	kg	JIS L1096 A-1	≥ 1.5
Crosswise	kg	JIS L1096 A-1	≥ 1.3

Note: Above values are mean values

JIS = Japanese Industrial Standard

1) inhouse test

2) inhouse test with HOREX gauge

(These values cannot be guaranteed and may be changed depending on market and production requirements)

Status : September 2017