

Technical Information

amaretta™ living - KX2678

Property	Unit	Standard	Data
Material- / Composition	%		Upper layer: ca.60 Polyamide ca.40 Polyurethane Lower layer: Cotton
Width	cm		130 or 140
Weight ¹	g/m ²		370±40
Thickness ²	mm		0.85±0.10
Breaking strength Lengthwise	kg/2.5 cm	JIS L1096	≥ 12
Crosswise	kg/2.5 cm	JIS L1096	≥ 8
Tear strength Lengthwise	kg	JIS L1096 A-1	≥ 1.5
Crosswise	kg	JIS L1096 A-1	≥ 1.5

Note: Above values are mean values

JIS = Japanese Industrial Standard

1) inhouse test

2) inhouse test with HOREX gauge

(These values cannot be guaranteed and may be changed depending on market and production requirements)

Status : August 2017